



# CONSTRUCTION MATERIALS

## TECHNOLOGIES

### LABORATORY TEST RESULTS

**Report for:** Derbigum - Imperbel  
 Parc Industriel  
 1360 Perwez - Belgium

**Attention:** Michel Getlichermann

<b>Description(s):</b> three (3) samples	<b>Manufacturer:</b> Derbigum - Imperbel
<b>Date Received:</b> Mar. 19, 2012	<b>Source:</b> Derbigum - Imperbel
<b>PRI-CMT Project No.:</b> PRSB-025-02-01	<b>Test Date(s):</b> Mar. 28, 2012

**Purpose:** The purpose of this testing was to determine the solar reflectance, thermal emittance, and solar reflectance index value of three (3) samples.

**Materials:** The samples for testing were received from Imperbel S.A.. The samples were labeled as indicated in the data table in the results section of this report.

**Test Methods:** The test methods used included ASTM C 1549-09: *Standard Test Method for Determination of Solar Reflectance Near Ambient Temperature Using a Portable Reflectometer* and ASTM C 1371-04a(2010)<sup>e1</sup>: *Standard Test Method for Determination of Emittance of Materials Near Room Temperature Using Portable Emissometers*. Both of these methods are Energy Star, Leadership in Energy and Environmental Design (LEED), and Cool Roof Rating Council (CRRC) approved methods for determining radiative properties.

The solar reflectance index (SRI) was calculated in compliance with ASTM E 1980-11: *Standard Practice for Calculating Solar Reflectance Index of Horizontal and Low-Sloped Opaque Surfaces*.

PRSB-025-02-01 PRI-CMT Accreditations: IAS TL-189; Miami-Dade 11-0429.05; Florida TST5878; Los Angeles TA24819; CRRC  
 The test results, opinions, or interpretations are based on the material supplied by the client. This report is for the exclusive use of stated client. No reproduction or facsimile in any form can be made without the client's permission. This report shall not be reproduced except in full without the written approval of this laboratory. PRI Construction Materials Technologies, LLC. assumes no responsibility nor makes a performance or warranty statement for this material or products and processes containing this material in connection with this report.


**Results:** All measurements were conducted at 72±3°F and 50±5%RH.

Sample ID	Solar Reflectance		Thermal Emittance		SRI		
	ASTM C 1549 <sup>1</sup>		ASTM C 1371 <sup>2</sup>		ASTM E 1980 <sup>3</sup>		
	Avg.	Std.Dev.	Avg.	Std.Dev.	Low-Wind	Medium-Wind	High-Wind
Derbibrte NT 1 with bitumen	0.806	0.002	0.88	0.00	100	100	100
Derbibrte NT 2 with bitumen	0.804	0.005	0.89	0.01	100	100	100
Derbibrte NT 3 with bitumen	0.806	0.002	0.89	0.01	100	100	100

Note(s): 1- Reflectance measurements were conducted using a Devices and Services SSR-ER Version 6.4 Reflectometer operated in v5 emulation mode and calibrated with Devices and Services Reference Tile # D-18.  
 2- Emittance measurements were conducted using a Devices and Services Emittance Model AE calibrated with Devices and Services Reference Standards: High Emittance: 0.90 and Low Emittance: 0.06.  
 3- SRI calculations per ASTM E 1980 utilize the following assumptions: Low-Wind  $h_c = 5 \text{ W/m}^2\cdot\text{K}$ , Medium-Wind  $h_c = 12 \text{ W/m}^2\cdot\text{K}$ , and High-Wind  $h_c = 30 \text{ W/m}^2\cdot\text{K}$ .

**Statement of Attestation:** The Solar Reflectance Index of these samples was calculated in accordance with **ASTM E 1980: Standard Practice for Calculating Solar Reflectance Index of Horizontal and Low-Sloped Opaque Surfaces**. The laboratory test results presented in this report are representative of the material supplied.

Signed: \_\_\_\_\_



**Brad Grzybowski**  
 Managing Director

Date: \_\_\_\_\_

March 29, 2012

**Report Issue History:**

Issue #	Date	Pages	Revision Description (if applicable)
Original	03/29/2012	2	NA

**END OF REPORT**

PRESB-025-02-01 PRI-CMT Accreditations: IAS TL-189; Miami-Dade 11-0429.05; Florida TST5878; Los Angeles TA24819; CRRC  
 The test results, opinions, or interpretations are based on the material supplied by the client. This report is for the exclusive use of stated client. No reproduction or facsimile in any form can be made without the client's permission. This report shall not be reproduced except in full without the written approval of this laboratory. PRI Construction Materials Technologies, LLC. assumes no responsibility nor makes a performance or warranty statement for this material or products and processes containing this material in connection with this report.